

Performance data Information

Figures indicated below are for guidance only

Polyca 1

Total solar energy rejected	78%
Ultra violet light rejected	99%
Glare reduction	88%

Polyca 5 Paint

Total solar energy rejected	29%
Ultra violet light rejected	98%
Glare reduction	27%
Standard color	white
Dry appearance	translucent matt
Spreading rate	approx 12.sq mtrs undiluted
Touch dry @20°C	approx 40mins
Recoating @20°C	approx 2 hours
Application methods	foam roller
Substrates	polycarbonate, glass, bitumen, plastics
Cleaning	clear water
Life expectancy	10 years
This product is more suited for commercial use only	
The first coat requires a paint thinner	